

TITANIUM DIOXIDE

TiOx-220

Product description

Product	Titanium Dioxide, Rutile pigment produced by the sulphate process.
Properties	The grade has a high whiteness, warm shade and good weather resistance.
Surface treatment	Si and Al compounds.
Applications	TiOx-220 is widely used in the production of various paints and plastics for interior and exterior use. Also, in varnish-and-paint systems based on organic solvents, which are used as industrial coatings or in architectural structures coloration. Field of application: decorative paper, silicone paints, solvent-borne paints, paints for road marking, powder paints, Plastics, PVC, masterbatches, and...
Product Information	Specification: TU 2321-001-17547702-2014, ISO 591-1:R2, ASTM D 476: Type III, CAS No.: 13463-67-7, EINECS No.:236-675-5

Physico-chemical

TiO ₂ , wt%	min. 93	ISO 591-1
Rutile content, %	min. 97	ASTM D 3720
Mean particle size, (d50)1, µm	max. 0.65	-
Top cut, (d95)1, µm	max. 1	-
Residue on a 45 µm sieve, wt%	max. 0.03	ISO 787-18
Specific gravity, g/cm ³	3.5	ISO 787-10
Moisture content, wt%	max. 0.5	ISO 787-2
pH of water suspension	6.5-8.5	ISO 787-9
Tint reducing power, arb. units	2000 - 2200	ISO 787-17
Color index	Pigment white 6	77891
Opacity, g/m ²	23 - 25	ISO 6504-3
Dispersibility, µm	max. 13	ISO 8780-4
Oil absorption, g/100g of pigment	18 - 22	ISO 787-5
Whiteness, arb. units	96.5 - 97.0	ISO 787-1
Brightness, L* (CIELAB)2	97.0 - 97.8	ISO 787-1
Yellowness, b* (CIELAB)2	2.0 - 2.5	ISO 787-1
Method of determination-Fritsch particle sizer analysette 22		
Method of determination- Powder tablet.		

Storage and packing

Store in dry covered warehouses.
The warranty period of storage: 12 months from the manufacturing date.
Paper bags (25 kg), Big bag containers (500, 1000 kg).

This information is a general description of product properties and their potential fields of application. The data is based on regularly conducted analyses of their properties and also on our own and our partner's experience of their application. Since the conditions of use are beyond our control, no warranty is given or to be implied in respect of such information.